

Test Q.C. Report


Report Date	4/5/2016	Customer			
Item Name	FB30-FS30	Item Type	Metal Buckles	Item Number	
Testing Type and Methods	Surface Inspection	Hardness (durometer)	System strength (ASTM-D3950)	Quantity	



Test Results

Date of Test		4/5/2016		Test number/Item	#1: FB30
Trial -No.	Surface	Hardness (HRC)	Breaking strength (daN) with		Remarks
			GW105PES-2000	GW105PES-2300	
1			2710	3379	
2				3455	
3				3350	
4				3317	
5				3335	
Average			<u>2710</u>	<u>3367</u>	

Date of Test		4/5/2016		Test number/Item	#2 FS30
Trial -No.	Surface	Hardness (HRC)	Breaking strength (daN) with		Remarks
			GW105PES-2000	GW105PES-2300	
1			3890	4222	
2			3872	4358	
3					
4					
5					
Average			<u>3881</u>	<u>4290</u>	

Approved by (Q.C. Manager):	Check by (Q.C. Supervisor):	Test By (Q.C. Inspector):
	Du Rong	Dong Ming